


**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

PA 1224246



REC'D 11 NOV 2004

WIPO

PCT

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

September 16, 2004

**THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM
THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK
OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT
APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A
FILING DATE UNDER 35 USC 111.**

APPLICATION NUMBER: 60/573,132

FILING DATE: May 21, 2004

**By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS**



N. Woodson
N. WOODSON
Certifying Officer

BEST AVAILABLE COPY

22783 U.S. PTO

PTO/SB/16 (10-01)

Approved for use through 10/31/2002. OMB 0651-0032
U.S. Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No.

ER573872387US

INVENTOR(S)					
Given Name (first and middle (if any))		Family Name or Surname		Residence (City and either State or Foreign Country)	
Thomas Jürgen		Mecklenburg Rohrmann		Butzbach, Germany Kelkheim, Germany	
<input type="checkbox"/> Additional inventors are being named on the _____ separately numbered sheets attached hereto					
TITLE OF THE INVENTION (500 characters max)					
MOLDING COMPOSITIONS COMPOSED OF A GLASS FIBER-REINFORCED OLEFIN POLYMER					
Direct all correspondence to: CORRESPONDENCE ADDRESS					
<input checked="" type="checkbox"/> Customer Number		34872		Place Barcode	
OR		Type Customer Number here		34872	
<input type="checkbox"/> Firm or Individual Name		William R. Reid		PATENT TRADEMARK OFFICE	
Address		Basell USA Inc.			
Address		912 Appleton Road			
City		Elkton	State	MD	ZIP 21921
Country		US	Telephone	410-996-1783	Fax 410-996-1560
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/> Specification Number of Pages		13		<input type="checkbox"/> CD(s), Number	
<input checked="" type="checkbox"/> Drawing(s) Number of Sheets		3		<input type="checkbox"/> Other (specify)	
<input type="checkbox"/> Application Data Sheet. See 37 CFR 1.76					
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT					
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27.				FILING FEE AMOUNT (\$)	
<input type="checkbox"/> A check or money order is enclosed to cover the filing fees					
<input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number:				08-2336	
<input type="checkbox"/> Payment by credit card. Form PTO-2038 is attached.				\$160.00	
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input checked="" type="checkbox"/> No.					
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____					

Respectfully submitted,

SIGNATURE



Date 05/21/2004

REGISTRATION NO.

(if appropriate)

Docket Number:

47,894

LU 6139-02 (US)

TYPED or PRINTED NAME William R. Reid

TELEPHONE 410-996-1783

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C. 20231.

EXPRESS MAILING CERTIFICATE


This certifies that the attached **Form PTO/SB/16** (in duplicate), **Specification (13 pages)** and **3 Sheets of Drawings** for the provisional application of **Thomas Mecklenburg et al.** for **MOLDING COMPOSITIONS COMPOSED OF A GLASS FIBER-REINFORCED OLEFIN POLYMER** (our ref: **LU 6139-02 (US)**) is being mailed by "Express Mail Post Office to Addressee" service in an envelope addressed:

Mail Stop Provisional Patent Application
Commissioner for Patents
P. O. Box 1450
Alexandria, VA 22313-1450

and deposited on **MAY 21, 2004** as "Express Mail" in the United States Postal Service, the number of the "Express Mail" mailing label being **ER573872387US**.

Douglas Jumps

Typed Name of Person Mailing Paper or Fee


Signature of Person

MOLDING COMPOSITIONS COMPOSED OF A GLASS FIBER-REINFORCED
OLEFIN POLYMER

The invention relates to a molding composition composed of an olefin polymer, in particular a propylene polymer, containing 5-50% by weight glass fibers which are bonded to the
5 olefin polymer by means of a compatibilizer, and from 10^{-4} to 1% by weight of a phthalocyanine pigment as the nucleating agent.

The reinforcement of olefin polymers with the aid of glass fibers has been known for some time. EP 663 418 A1 describes, for example, a polypropylene molding composition which is reinforced with glass fibers. However, to obtain good mechanical properties, it is necessary to
10 use compatibilizers or coupling agents which ensure good binding of the glass fibers to the polyolefin matrix. The compatibilizers frequently comprise firstly a reactively modified polymer which is compatible with the matrix polymer as a coupler, and secondly a compound having reactive polar groups which can bond both to the glass fibers and to the coupler.

It is likewise generally customary to nucleate unreinforced polymers of propylene to
15 improve the stiffness and strength, but also the transparency, of the molding produced therefrom. To this end, in addition to sodium benzoate, fine talc, phosphate ester salts, sorbitols, quinacridone pigments and others, phthalocyanine pigments are also used as nucleating agents. The nucleation generally leads to an improvement in the tensile strength and stiffness, but not to a significant improvement in the impact strengths, and often to a reduced yield elongation and
20 tensile strain at break.

In Polymer 34, 4747 (1993) and in European Polymer Journal 32, 1425 (1996), the influence of nucleation on polypropylene-glass fiber composites using sodium benzoate as a nucleating agent was investigated. For the nucleated glass fiber composites, a modulus of elasticity increased by 10% and tensile strength increased by 10% compared to the nonnucleated
25 composites was found.

The sodium benzoate, and also many other nucleating agents, as a consequence of their polar character which improves the nucleation, have the disadvantage that they can react with the coupler of the compatibilizer and thus interfere with the binding of the glass fibers, or, as a consequence of their high cost, are of little economic attractiveness.

A particular disadvantage of nucleating agents such as sodium benzoate is the only moderate hot water resistance and vapor resistance of the polyolefin molding compositions, especially in the case of long-term contact over several weeks or months.

It is an object of the present invention to provide a polyolefin molding composition which exhibits improved matrix binding of the glass fibers and therefore better mechanical properties and is obtainable inexpensively and has improved resistance to hot water, especially in the presence of detergents.

We have found that this object is achieved, surprisingly, by the combination of glass fibers which are bonded to the olefin polymer by means of a compatibilizer, and a phthalocyanine pigment, which allows particularly good matrix binding of the glass fibers in the matrix polymer, in particular propylene polymer, to be achieved. Accordingly, the molding compositions according to the invention comprise an olefin polymer containing 5-50% by weight of glass fibers and from 10^{-4} to 1% by weight, preferably from 10^{-3} to $10^{-1}\%$ by weight, of a phthalocyanine pigment as a nucleating agent. The low costs of the phthalocyanine pigment and the fact that even a very small fraction of the phthalocyanine pigment in the polymer leads to sufficient nucleation ensures extremely inexpensive production. In addition, the polyolefin molding composition features excellent hot water resistance.

Essential for the polyolefin molding composition according to the invention is firstly the content of from 5 to 50% by weight of glass fibers based on the overall composition. The glass fibers may be either cut glass fibers having a length of from 3 to 6 mm or long glass fibers, although preference is given to using cut glass fibers. Preference is further given to using from 10 to 40% by weight, more preferably from 20 to 40% by weight, of glass fibers.

Preference is given to using cut glass fibers, also known as chopped strands. When cut glass fibers are used, it is possible to attain by nucleation the stiffness of molding compositions comprising long glass fibers at a distinctly more favorable price. The glass fibers used preferably have a length of from 3 to 6 mm, more preferably from 3 to 4.5 mm, and a diameter of from 10 to 20 μm , preferably from 12 to 14 μm . Depending on the compounding and injection molding conditions, the length of the glass fibers in the molding composition (granules or injection-molded finished particles) is from 50 μm to 3 000 μm , preferably from 50 to 1 000 μm .

To bind glass fibers to the polyolefin matrix, a polar-functionalized compatibilizer is used. One type which can be used is low molecular weight compounds which serve exclusively

to make the glass fibers less hydrophilic and therefore more compatible with the polymer.

Suitable compounds are, for example, silanes such as aminosilanes, epoxysilanes, amidosilanes or acrylosilanes. However, the compatibilizers preferably comprise a functionalized polymer and a low molecular weight compound having reactive polar groups. The functionalized polymer is preferably graft or block copolymers which are compatible with the matrix polymer. For a propylene homopolymer as the matrix component, preference is given, for example, to using a graft or block copolymer of propylene as the functionalized polymer.

In this context, preference is given to those polymers whose reactive groups are acid anhydrides, carboxylic acids, carboxylic acid derivatives, primary and secondary amines, hydroxyl compounds, oxazolines and epoxides, and also ionic compounds. Particular preference is given to using a propylene polymer grafted with maleic anhydride as the functionalized polymer. The low molecular weight compound serves to couple the glass fiber to the functionalized polymer and thus to bind it securely to the polyolefin matrix. These are usually bifunctional compounds, in which case one functional group can enter into a binding interaction with the glass fibers and the second functional group can enter into a binding interaction with the functionalized polymer. The low molecular weight compound used is preferably an amino- or epoxysilane, more preferably an aminosilane. The aminosilanes bond with the silane hydroxyl groups to the glass fiber, while the amino groups form a stable amide bond, for example with polypropylene grafted with maleic anhydride.

The compatibilizers can be used preprepared or prepared in situ. It is particularly advantageous to apply the low molecular weight component to the glass fibers before it is incorporated into the polyolefin matrix. The functionalized polymer can be generated in situ in a simple manner by reactive extrusion of the matrix polymer, for example with maleic anhydride. It is also possible to use a masterbatch which comprises the glass fibers and the compatibilizer in premixed form.

It is also essential to the present invention that the glass fiber-reinforced polypropylene molding composition is nucleated with a phthalocyanine pigment. The phthalocyanine pigments themselves are well known and are derived from the basic phthalocyanine structure by incorporating a central metal ion and by substituting the phthalocyanine ring. In practice, the central atoms used in the pigments are copper, nickel and cobalt, and copper is the preferred central atom. The basic phthalocyanine structure may optionally be substituted, in particular

with chlorine or bromine atoms. Substitution with organic radicals can also be carried out to adapt the nucleation properties. Suitable phthalocyanine pigments are, for example, unsubstituted copper-phthalocyanine (phthalocyanine blue), polychlorinated copper-phthalocyanine (phthalocyanine green, $C_{32}H_2N_8Cl_{14}Cu$), cobalt-phthalocyanine ($C_{32}H_{16}N_8Co$),
5 nickel-phthalocyanine ($C_{32}H_{16}N_8Ni$). Particular preference is given to unsubstituted copper-phthalocyanine.

Unsubstituted copper-phthalocyanine and polychlorinated copper-phthalocyanine are sold, for example, by Clariant, Frankfurt, DE under the names PV Echtblau and PV Echtgrün respectively.

10 The proportion of nucleating agent is between 10^{-4} and 1% by weight, based on the overall composition. Preference is given to using from 10^{-3} to $10^{-1}\%$ by weight, particular preference to from $5 \cdot 10^{-3}$ to $5 \cdot 10^{-2}\%$ by weight, of the nucleating agent.

The combination of glass fiber reinforcement and nucleation with phthalocyanine pigments results in a molding composition which is improved over the prior art with regard to
15 the stiffness and toughness. In addition, the adhesion of the glass fibers to the polymer matrix is surprisingly distinctly improved with the same compatibilizer, which results in an improvement in the propagation of cracks in the molding composition. In addition, the nucleation with phthalocyanine pigments surprisingly results in distinctly improved long-term stabilities in the tensile strengths and impact strengths in hot water and hot detergents, for example over testing
20 times of 1 000 hours at 95°C, compared to nonnucleated glass fiber-reinforced comparative specimens. Advantages in the long-term stability of the inventive molding compositions can also be recognized, for example, in the long-term tests in aqueous detergents in accordance with the UL standards 2157 and 749, testing over 138 days at 82°C.

The particular advantage of the phthalocyanine pigment is that it is substantially
25 compatible with the customary compatibilizers, i.e. there is no or hardly any mutual interference between the action of nucleating agent and compatibilizer.

The molding compositions according to the invention are obtainable by melting and mixing the olefin polymer with the phthalocyanine pigments and the glass fibers, and the mixing is effected in a mixing apparatus at temperatures of from 180 to 320°C, preferably from 200 to
30 280°C, more preferably from 220 to 260°C. Useful mixing apparatus in this context is in particular extruders or kneaders, and particular preference is given to twin-screw extruders. In

the case of polymers present in powder form, it is appropriate to premix the polymer with the nucleating agent, and also any other additives, at room temperature in a mixing apparatus. The olefin polymer may be mixed with the nucleating agent and the glass fibers in one step or else in a plurality of steps. Preference is given to initially melting the olefin polymer with the
5 nucleating agent and further additives in the mixing apparatus, and to mixing them, and subsequently mixing the glass fibers with the melt, in order to reduce the abrasion in the mixing apparatus and the fiber breakage.

Useful matrix components of the molding composition according to the invention are homopolymers and copolymers of alpha-olefins having from 2 to 12 carbon atoms, for example
10 of ethylene, propene, 1-butene, 1-hexene or 1-octene. Also suitable are copolymers and terpolymers which, in addition to these monomers, contain further monomers, in particular dienes, for example ethylidenenorbornene, cyclopentadiene or butadiene.

Preferred matrix components are polyethylene, polypropylene, polybutylene and/or copolymers of ethene with propene, 1-butene, 1-hexene or 1-octene. In principle, any
15 commercially available type thereof can be used. Useful types include, for example: linear polyethylene of high, moderate or low density, LDPE, ethylene copolymers having small amounts (up to a maximum of approx. 40% by weight) of comonomers such as propene, 1-butene, 1-hexene, 1-octene, n-butyl acrylate, methyl methacrylate, maleic anhydride, styrene, vinyl alcohol, acrylic acid, glycidyl methacrylate, and the like, isotactic or atactic
20 homopolypropylene, random copolymers of propene with ethene and/or 1-butene, ethylene-propylene block copolymers and the like. Such polyolefins may also contain an impact strength component, for example EPM or EPDM rubber, or SEBS.

When polyethylene is used as the matrix component, the comonomer content of the ethylene copolymer should not exceed 1 mol% of the total amount of monomers used. Preferred
25 comonomers are 1-olefins, and particularly preferred comonomers are 1-butene, 4-methyl-1-pentene, 1-hexene and 1-octene. The polyethylene may also be a blend of two or more polyethylene components.

Particular preference is given to using a propylene polymer as the matrix component. The propylene polymer used may in particular be a propylene homopolymer or else a propylene
30 copolymer having up to 30% by weight of other olefins having up to 10 carbon atoms in copolymerized form. Such other olefins are in particular C₂-C₁₀-1-alkenes such as ethylene, 1-

butene, 1-pentene, 1-hexene, 1-heptene or 1-octene, and preference is given to using ethylene, 1-butene or ethylene and 1-butene. Particular preference is given to using propylene homopolymers.

In this context, the copolymers of propylene are block or impact copolymers or preferably random copolymers. When the copolymers of propylene have a random structure, they generally contain up to 15% by weight, preferably up to 6% by weight, more preferably up to 2% by weight, of other olefins having up to 10 carbon atoms, in particular ethylene, 1-butene or a mixture of ethylene and 1-butene, as comonomers. The block or impact copolymers of propylene are polymers in which, in the first stage, a propylene homopolymer or a random copolymer of propylene having up to 15% by weight, preferably up to 6% by weight, more preferably up to 2% by weight, of other olefins having up to 10 carbon atoms as comonomers is prepared and then, in the second stage, a propylene-ethylene copolymer having ethylene contents of from 15 to 99% by weight, the propylene-ethylene copolymer additionally being able to contain further C₄-C₁₀-olefins, is polymerized thereto. In general, sufficient propylene-ethylene copolymer is polymerized thereto that the copolymer generated in the second stage has a content in the end product of from 3 to 90% by weight. The random copolymers of propylene are polymers in which, in the first stage, a propylene homopolymer or a random copolymer of propylene having up to 15% by weight, preferably up to 6% by weight, more preferably up to 2% by weight, of other olefins having up to 10 carbon atoms as comonomers is prepared and then, in the second stage, a propylene homopolymer or a random copolymer of propylene having up to 15% by weight, preferably up to 6% by weight (more preferably up to 2% of comonomers) of other olefins having up to 10 carbon atoms is polymerized thereto. The polymers of the two stages differ in the molar mass and the comonomer content. The ethylene content of the blend is 15% by weight or preferably up to 6% by weight and more preferably up to 3% by weight, of comonomers.

Preference is given to using isotactic polypropylene having a xylene-insoluble fraction of over 95%, preferably of over 97%. The polyolefin generally has an MFR (230°C/2.16 kg) of from 0.2 to 200 g/10 min to ISO 1133, preferably between 0.5 and 100 g/10 min and more preferably between 2 and 30 g/10 min. Preference is further given to polypropylene molding compositions having a monomodal molar mass distribution.

The molding compositions according to the invention may also comprise customary additives and auxiliaries, for example stabilizers against damaging processing effects, antioxidants against heat oxidation and aging, UV action, neutralizing agents, fillers, organic and inorganic pigments or pigment preparations, for example carbon black dispersions in polyolefins, 5 antistats, nonpolar waxes or specific low molecular weight glidants and lubricants. UV stabilizers, especially monomeric and oligomeric HALS, antistats and polar waxes and also stearates are less suitable for the inventive molding compositions, or, if at all, in very low concentrations, since they may likewise react with the coupler of the compatibilizer and thus reduce the efficiency of the coupling. However, the amount of additives and auxiliaries should 10 not exceed 10% by weight based on the total amount of the material, preferably 5% by weight. For visual reasons, it may also be advisable to add appropriate suitable color pigments to the molding compositions according to the invention and color them to another, preferably darker color.

The olefin polymers used in the molding compositions according to the invention can be 15 obtained with all common processes and catalysts. Preference is given to polymerizing the appropriate monomers by means of a Ziegler-Natta catalyst, of a Phillips catalyst based on chromium oxide or of a metallocene catalyst. In this context, metallocenes are complexes of metals of groups 3 to 12 of the Periodic Table with organic ligands which, together with metallocenium ion-forming compounds, result in effective catalyst systems.

20 To prepare the olefin polymers, the customary reactors used for the polymerization of C₂-C₁₀-olefins can be used. Suitable reactors include continuous horizontal or vertical stirred tanks, circulation reactors, loop reactors, stage reactors or fluidized bed reactors. The size of the reactors is of no great importance for the preparation of the molding compositions according to the invention. It depends on the output which is to be achieved in the individual reaction zone or 25 zones. The polymerization process can be carried out in one or more stages. The polymerization can be effected in the gas phase, in bulk or suspension or a combination thereof.

The molding composition according to the invention is suitable in particular for the production of motor vehicle parts which place high demands on the stiffness and toughness of the material. It is particularly advantageous to use it in motor vehicle parts which are dark- 30 colored or provided with a decorative layer, for example front ends or dashboard supports, in which the blue coloration caused by the phthalocyanine pigment is covered. Moldings produced

from the molding composition according to the invention are suitable, as a result of their improved stiffness and toughness even when cut glass fibers are used, for applications which have hitherto been reserved for long fiber-reinforced propylene polymers.

The molding composition according to the invention also features very good durability toward hot water and detergents. They can therefore be used particularly advantageously as the material for moldings which are exposed to contact with hot water, wash and rinse liquors and other aggressive materials. The present invention therefore further provides the use of the molding composition according to the invention as a wash liquor vessel (preferably not visible) in washing machines, and also wash liquor vessels produced from the molding composition according to the invention, but also the use for water and liquor pump casings.

Example 1

a) Preparation of the glass fiber-reinforced polypropylene molding composition:

The following proportions by weight are based in each case on the total mass of the polymer molding composition, unless stated otherwise.

69.19% by weight of polypropylene homopolymer (Moplen HP500H, Basell Polyolefine, Germany, MFR (230°C, 2.18 kg) = 1.2 g/10 min) was admixed in a twin-screw extruder (ZSK 53) with 30% by weight of a short glass fiber (ECS 03T-T480 chopped strands, NEG) having a length of 3 mm and a diameter of 13 µm. This was done by metering the short glass fibers into the polymer molding composition melt at element 3 or 4 of the 10-section twin-screw extruder. 0.01% by weight of phthalocyanine blue 15:3 (PV-Echtblau 2GL SP, Clariant) as a nucleating agent, 1.2% by weight of Polybond 3200 (from Crompton) as a compatibilizer, 0.1% by weight of an inorganic acid scavenger and 0.5% by weight of a stabilizer combination composed of a phenolic antioxidant, distearyl thiodipropionate and a di-tert-butylphenyl phosphite were simultaneously also added to the polypropylene homopolymer.

b) Hot water test

The polypropylene molding composition from example 1 was processed in an injection molding machine to give specimens in accordance with DIN EN ISO 527-2 and DIN EN ISO 179/1.

The tensile stress at break and the tensile modulus of elasticity of the samples were determined to ISO 527-01 and -1. In addition, the Charpy impact strength was measured in accordance with DIN EN ISO 179/1eU.

The specimens were introduced into demineralized water at a temperature of 95°C in a heatable bath. Depending on the application and requirements, different detergents may also be added with defined concentrations.

After the appropriate time, in each case at least 5 specimens were taken and the tensile stress at break and the tensile modulus of elasticity to DIN EN ISO 527-2 determined as the average of 5-10 individual measurements. In the same way, the Charpy impact strength was determined to DIN EN ISO 179/1eU.

The test results are compiled in tables 1 to 3 and in figures 1 to 3.

Example 2

Example 1 was repeated with a content of 0.05% by weight of phthalocyanine blue 15:3 (PV-Echtbau 2GL SP, Clariant). The amount of polypropylene was adjusted for a combined total mass of the polymer molding composition of 100% by weight.

Comparative example 3

Example 1 was repeated with a content of 0.1% by weight of sodium benzoate as a nucleating agent. The amount of polypropylene was adjusted for a combined total mass of the polymer molding composition of 100% by weight.

Comparative example 4

Example 1 was repeated with a content of 0.3% by weight of sodium benzoate as a nucleating agent. The amount of polypropylene was adjusted for a combined total mass of the polymer molding composition of 100% by weight.

Table 1: Tensile stress at break as a function of the duration of the hot water contact				
Test duration [days]	Tensile stress at break [MPa]			
	Example 1 [◆]	Example 2 [□]	Comparative example 3 [▽]	Comparative example 4 [○]
0	82.6	88.2	91.9	92.5
1	81.5	87.0	82.1	81.5
3	81.7	87.4	77.2	72.9
5	79.4	84.7	70.2	66.2
10	78.5	82.8	65.1	59.8
20	73	76.5	57.4	50.6
30	71.5	73.8	55.0	48.4
40	69.4	71.4	53.4	48.4

Table 2: Tensile modulus of elasticity as a function of the duration of the hot water contact				
Test duration [days]	Tensile modulus of elasticity [MPa]			
	Example 1 [◇]	Example 2 [□]	Comparative example 3 [▽]	Comparative example 4 [○]
0	6615	6692	6659	6679
1	6400	6530	6467	6440
3	6518	6670	6636	6514
5	6463	6607	6424	6284
10	6523	6579	6373	6134
20	6102	6239	5903	5445
30	6174	6373	6077	5570
40	6091	6134	5923	5496

Table 3: Charpy impact strength as a function of the duration of the hot water contact				
Test duration [days]	Charpy impact strength [kJ/m²]			
	Example 1 [◇]	Example 2 [□]	Comparative example 3 [▽]	Comparative example 4 [○]
0	42.1	45.7	49.0	48.1
1	31.7	32.8	25.0	24.4
3	28.7	30.4	21.1	18.3
5	24.7	28.7	17.0	17.9
10	24.7	25.9	15.7	16.2
20	21.0	21.5	14.1	16.9
30	19.8	19.3	14.4	16.0
40	18.3	17.7	14.7	17.4

It can be seen that the fall in tensile stress at break and in the tensile modulus of elasticity and also in the Charpy impact strength is surprisingly lower in the case of the glass fiber-reinforced polypropylene molding compositions nucleated with phthalocyanine (symbols ◇ and □) than in the case of those nucleated with sodium benzoate (symbols ▽ and ○).

We claim:

1. A molding composition composed of an olefin polymer containing
 - a) from 5 to 50% by weight of glass fibers which are bonded to the olefin polymer by means of a compatibilizer, and
 - 5 b) from 10^{-4} to 1% by weight, in particular from 10^{-3} to $10^{-1}\%$ by weight, of a phthalocyanine pigment as a nucleating agent.
2. A molding composition as claimed in claim 1, wherein the olefin polymer is a propylene polymer.
3. A molding composition as claimed in claim 1 or 2, wherein the glass fibers are cut glass
10 fibers.
4. A molding composition as claimed in any of claims 1 to 3, comprising from 10 to 40% by weight, in particular from 20 to 40% by weight, of glass fibers.
5. A molding composition as claimed in any of claims 1 to 4, wherein the compatibilizer comprises an olefin polymer, in particular a propylene polymer, functionalized with polar
15 groups.
6. A molding composition as claimed in claim 5, wherein the functionalized compatibilizer comprises an olefin polymer grafted with maleic anhydride and an aminosilane or epoxysilane.
7. A molding composition as claimed in any of claims 2 to 6, wherein the propylene polymer is a propylene homopolymer.
- 20 8. A molding composition as claimed in any of the preceding claims, wherein the olefin polymer has a melt-mass flow rate to ISO 1133 at 230°C and 2.16 kg of between 0.5 and 100 g/10 min, preferably between 2 and 30 g/10 min.
9. A process for producing molding compositions as claimed in any of the preceding claims, wherein, in a mixing apparatus, the propylene polymer is initially melted and mixed with the
25 nucleating agent at temperatures of from 180 to 320°C, and the glass fibers are subsequently mixed with the melt.
10. The use of the molding compositions as claimed in any of claims 1 to 8 as moldings for automobile construction or as a wash liquor vessel, water pump casing and liquor pump casing.
11. A wash liquor vessel, water pump casing and liquor pump casing obtained from the
30 molding compositions as claimed in any of claims 1 to 8.

LU 6139-02 (US)

12. A motor vehicle part, in particular a covering part of a motor vehicle, obtained from the molding compositions as claimed in any of claims 1 to 8.

Abstract

The invention relates to a glass fiber-reinforced molding composition composed of an olefin polymer, in particular a propylene polymer. The molding composition comprises an olefin polymer which contains 5-50% by weight of glass fibers which are bonded to the olefin polymer
5 by means of a compatibilizer, and from 10^{-4} to 1% by weight, preferably from 10^{-3} to 10^{-1} % by weight, of a phthalocyanine pigment as the nucleating agent. The low costs and the fact that even a very small fraction of the phthalocyanine pigment in the polymer leads to sufficient nucleation ensures extremely inexpensive production. The nucleation with the phthalocyanine pigment leads to an improvement in the impact strength, and also in the yield stress and tensile
10 strain at break of the molding composition.

Fig. 1




Fig. 2




Fig. 3

